Frosted Privacy Film - Reeded Glass

FRYYC95A

Frosted Privacy Film - 'Reeded Glass' FRYYC95A, is a PET frosted privacy film with a 13mm wide fluted pattern, this has a permanent adhesive and a PET release liner. This two-way privacy film has a visible light transmission (VLT) of 95%, giving a privacy level of 3/5 and 99% UV reduction. This film should be wet applied to glass or can be used on acrylic surfaces with a barrier used underneath. Not suitable for printing.

Face Film	PET
Adhesive	Transparent, permanent pressure sensitive adhesive, solvent polyacrylate
Liner	Single-sided silicone-coated polyester
Shrinkage	x direction ≦0.1%, y direction ≦0.1% FTM14
Service Temperature	5.0°F to 140.0°F
Shelf Life	2 years under normal conditions at a temperature of 71.6°F and relative humidity of 50-55%

Application Recommendations

- This material is suitable for **wet application method only**. Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination.
- **Not to be applied** to fresh paint or ink, polycarbonate, rubber, plastic mouldings and certain PVCs. In case of doubt, please test prior to final application. The film must not touch the rubber window moulding. If two panels meet side by side on a window, carefully trim the film so that the panels meet and form a butt seam. Do not overlap the panels.
- Window film may be washed with common washing solutions, **24 hours after installation**. Abrasive type cleaning agents and bristle brushes which would scratch the film must not be used. Synthetic sponges, squeegees, or soft cloths are recommended to be used with the cleaning solution.
- Also, **do not use any other adhesive products on the film**.
- **Reeded films have a directional texture (the vertical "reeds"). If you rotate a panel 90° or 180°:**
- The flutes will run in a different direction, changing the light-diffusion and privacy effect.
- Adjacent panels will look mismatched, even if the pattern spacing is the same.
- When sunlight hits the glass, the rotated panel will reflect and refract differently, making the join very obvious.
- When installing multiple panels next to one another always cut the same edge of the roll. Aim to 'finish' the previous flute to avoid changes in the pattern across the installation.

This document is intended as a source of information, is given without guarantee, and does not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of the product for their specific intended purpose.

2.76 mils

Film Thickness

3/5
95% VLT

Privacy Level

based on 3mm glass

50.0°F
min

Application temp

5
years

Durability

on static applications

Peel Adhesion

Printed film on glass, typical value

36.52oz/in

20 mins

43.83oz/in

24 hours

Contra Vision Supplies Limited,
Victoria House, 19–21 Ack Lane East, Bramhall,
Stockport, SK7 2BE, United Kingdom

Tel. +44 161 439 9307
Email: technical@contravision.com
www.contravision.com

© Copyright Contra Vision Supplies Limited 2026

All trademarks in this datasheet are © Contra Vision Ltd

Frosted Privacy Film - Reeded Glass
FRYYC95A

Fire rating

ASTM E84 Certificate(s) can be found at **https://www.contravision.com/privacy-window-film/privacy-window-film-datasheets/**

Solar performance

Based on 1/8" glass	No film	Reeded
Visible light transmission	90%	95%
Visible light reflection, exterior	8%	2%
Visible light reflection, interior	8%	2%
UV transmission	40%	40%
Solar energy transmission	83%	92%
Solar energy reflection	8%	3%
Solar energy absorption (total)	9%	4%
Glare reduction	0%	-
G value	0.86	0.94
Shading coefficient (SC)	1	1.08

Durability

Durability stated is for unprinted and untreated material correctly applied to an inert, vertical substrate subject to MidEuropean weathering conditions. Some printing inks and drying or curing regimes may reduce the expected lifetime of the printed graphic. Please consult your ink manufacturer for guidance. Incorrect application methods, inadequate window cleaning and preparation and incompatible window treatments may reduce the expected lifetime of the applied material whether printed or unprinted, overlaminated or unlaminated. Mechanically sustained damage, chemical damage and UV-degradation to printed, unprinted, laminated or unlaminated material may also reduce expected durability.

Zone 1; 5 years (inside) / 3 years (outside) (North America, Canada & Patagonia)
Zone 2; 4 years (inside) / 2 years (outside) (Argentina, Chile, Paraguay, Uruguay)
Zone 3; 3 years (inside) / 1 years (outside) (Bolivia, Brazil, Caribbean Islands, Central America, Mexico, Peru)

For more information on zones and a map of the regions, please visit **https://www.contravision.com/print-substrates/datasheets/**

Environmental

For further information on the environmental benefits of using Contra Vision products and the efforts we're making to improve the sustainability of our material, you can search for "sustainability" on our website.

Substrate

This product is not recommended for use on the inside of triple glazed windows or glass with coatings such as anti-reflective, selfcleaning and scratch-resistance, which may be damaged during film removal.

Other information

For further information visit the Contra Vision Technical Hub at **https://www.contravision.com/print-substrates/technical-hub**

Contra Vision Supplies Limited,
Victoria House, 19–21 Ack Lane East, Bramhall,
Stockport, SK7 2BE, United Kingdom

Tel. +44 161 439 9307
Email: technical@contravision.com
www.contravision.com

© Copyright Contra Vision Supplies Limited 2026

All trademarks in this datasheet are © Contra Vision Ltd