Advance™ White on Black

WBYRG40A

Advance™ WBYRG40A is a White on Black 'PVC-free' perforated self-adhesive vinyl with 40% transparency; and a removable, pressure-sensitive adhesive, featuring a Replacement Liner with Grayliner™ technology. This film allows an image to be seen on the outside of a window while allowing viewing through from the inside. This product is not suitable for curved surfaces, the matching PVC product should be specified instead. This promotional film features an unperforated paper liner and is intended for latex, solvent and 'eco-solvent' inkjet printing only.

Face Film	Cool White on Black PET
Face Film Weight	2.89oz/yard^2
Adhesive	Transparent, removable, solvent polyacrylate
Adhesive Weight	0.83oz/yard^2±0.09oz/yard^2
Liner	Unperforated Replacement Liner. White paper: grey, PE and silicone coated on top side, backprinted with Contra Vision® Advance™ branding and PE coated on the back side.
Liner Weight	4.72oz/yard^2±0.29oz/yard^2
Removability	Minimum 12 months clean removability without adhesive residue at ambient temperature Performance may be affected in Zone 2 & 3 regions
Shrinkage	x direction ≦0.1%, y direction ≦0.1% FTM14
Service Temperature	-13.0°F to 149.0°F
Shelf Life	2 years under normal conditions at a temperature of 71.6°F and relative humidity of 50-55%

Print Types

- Solvent
- Eco-Solvent
- Latex or Resin

Application Recommendations

- Apply the film using a **dry application method**.
- Clean surfaces thoroughly to clear from dust, grease or any contamination; final clean with soap and water, rinse, and dry.
- **Not to be applied** to fresh paint, ink, polycarbonate, rubber, plastic moldings, and certain PVCs—in case of doubt, test prior to final application.
- Recommended for flat or gently curved surfaces only.
- Cut film back at least 1/8" from any edges so the film finishes on a flat surface.
- Film **must not touch** rubber window moldings.
- Trim side-by-side panels to form a butt seam—**do not overlap.**
- Follow minimum application temperature and avoid washing within 24 hours of application.

Printing Recommendations

Replacement Liner construction is not recommended for use with UV curing inkjet printers. Depending on the brand of ink and density of the print, "bridging" can occur over the perforated holes after removal of the Replacement Liner, in relatively dark areas of a design. This is eliminated with Universal Liner. We therefore recommend Universal Liner for UV inkjet printing. After printing the ink must be thoroughly dry, including in the perforated holes in order to avoid any contamination, particularly during lamination.

Certified for HP Latex Inks

Search our database for all Contra Vision profiles
https://www.contravision.com/print-substrates/print-profiles-register/

This document is intended as a source of information, is given without guarantee, and does not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of the product for their specific intended purpose.

3.94 mils ±0.39 mils
Film Thickness

40% ø0.06 in
Transparency

39.2°F min
Application temp

1 - 2 years
External durability
on static applications
See next page for more info

Peel Adhesion

Printed film on glass, typical value

10.96oz/in
20 mins

14.61oz/in
24 hours

Contra Vision Supplies Limited,
Victoria
House, 19–21 Ack Lane East, Bramhall,
Stockport, SK7 2BE, United Kingdom

Tel. +44 161 439 9307
Email: technical@contravision.com
www.contravision.com

© Copyright Contra Vision Supplies Limited 2026

All trademarks in this datasheet are © Contra Vision Ltd

Advance™ White on Black
WBYRG40A

Fire rating

ASTM E84

Certificate(s) can be found at **https://www.contravision.com/print-substrates/datasheets/**

Solar performance

Based on 1/8" glass	No film	40% Transparency
Visible light transmission	90%	36%
Visible light reflection, exterior	8%	51%
Visible light reflection, interior	8%	11%
UV transmission	40%	16%
Solar energy transmission	83%	33%
Solar energy reflection	8%	51%
Solar energy absorption (total)	9%	16%
Glare reduction	0%	60%
G value	0.86	0.344
Shading coefficient (SC)	0.86	0.40

Durability

Durability stated is for unprinted and untreated material correctly applied to an inert, vertical, static (nonvehicular) substrate which is subject to Mid-European weathering conditions. Some printing inks and drying or curing regimes may reduce the expected lifetime of the printed graphic. Please consult your ink manufacturer for guidance. Incorrect application methods, inadequate window cleaning and preparation and incompatible window treatments may reduce the expected lifetime of the applied material whether printed or unprinted, overlaminated or unlaminated. Mechanically sustained damage, chemical damage and UV-degradation to printed, unprinted, laminated or unlaminated material may also reduce expected durability. There may be some discolouration with prolonged exposure to sunlight. All perforated window films are especially vulnerable to damage along the edges and corners, which may lead to premature failure.

Zone 1; 2 years (outside) (North America, Canada & Patagonia)
Zone 2; 1 years (outside) (Argentina, Chile, Paraguay, Uruguay)
Zone 3; 1 years (outside) (Bolivia, Brazil, Caribbean Islands, Central America, Mexico, Peru)

For more information on zones and a map of the regions, please visit **https://www.contravision.com/print-substrates/datasheets/**

Regulations

Some countries and regions have laws or regulations requiring minimum light passage that may limit or preclude the use of this product on vehicle windows. The user is responsible for determining and complying with all applicable standards.

Environmental

Contra Vision Advance™ perforated window film is PVC free, therefore contains no phlatates and conforms to the latest REACH regulations - please refer to our website for further details. Contra Vision packaging is produced from recycled cardboard, with polypropylene end bungs and polyethylene wrapping. All of which are fully recyclable, subject to local recycling facilities. For further information on the environmental benefits of using Contra Vision products and the efforts we're making to improve the sustainability of our material, you can search for "sustainability" on our website.

Substrate

This product is not recommended for use on glass with coatings such as anti-reflective, self-cleaning and scratch-resistance, which may be damaged during film removal.

Other information

For further information visit the Contra Vision Technical Hub at **https://www.contravision.com/print-substrates/technical-hub**

Contra Vision Supplies Limited,
Victoria
House, 19–21 Ack Lane East, Bramhall,
Stockport, SK7 2BE, United Kingdom

Tel. +44 161 439 9307
Email: technical@contravision.com
www.contravision.com

© Copyright Contra Vision Supplies Limited 2026

All trademarks in this datasheet are © Contra Vision Ltd